(21) Application No.202341050321 A

(19) INDIA

(22) Date of filing of Application :26/07/2023

(43) Publication Date: 01/09/2023

## (54) Title of the invention: SOIL STABLIZATION BY REUSING MICRO HYBRID GEOSYNTHETIC FIBERS

:B32B0005020000, G01N0003240000, A61K0036899000, (51) International classification G06F0030150000, A01G0022000000 (86) International Application No :PCT// :01/01/1900 Filing Date (87) International Publication No : NA (61) Patent of Addition to :NA Application Number :NA Filing Date (62) Divisional to Application :NA Filing Date

(71)Name of Applicant:  1)St. Martin's Engineering College Address of Applicant:St.Martin's Engineering College, Dhulapally Kompally Secunderabad
Name of Applicant : NA Address of Applicant : NA (72)Name of Inventor : 1)Mr. Patil Abhishek Assistant Professor, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
2)Ms. Sandhya Kiran J K Assistant Professor, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
3)Dr. P. Santosh Kumar Patra Principal, SMEC Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
4)N. Shiva SaiGoud Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
5)D. Sulochana Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
6)B. Vijay Kireeti Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
7)B. Rakesh Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
B)G. Dhanush Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
9)T. S. Somashekar Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
- 10)Y. Gopikiran Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
- 11)B. Shiva Raj Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
- 12)Ch. Madhuri Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
- 13)A. Manideep Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad
14)B. Nithinrao Student, CE Address of Applicant :St.Martin's Engineering College, Dhulapally Kompally Secunderabad

## (57) Abstract:

The IRC SP: 20-2002 pavement design catalogues were used to determine the pavement thickness. When compared to the liquid limit of the soil alone, the liquid limit of the soil with the addition of bamboo fibres was shown to be decreasing. The addition of fibres reduced the soil's plastic limit. With more fibres present, the soil's maximum rate of shrinkage rose. Adding bamboo fibres to soil increases MDD by weight of soil up to 0.75% before it starts to decline, which also lowers the equivalent OMC. A 36.5% liquid limit for the soil alone was discovered. The MDD of the soil with addition of 0.5%, 1.0%, and 1.0% bamboo fibres by weight of soil is found to be increased by 0.11%, 16.98%, and 33.75%, respectively, while the corresponding OMC is decreased by 15.62, 21.8, and 33.75%. With the addition of 0.25%, 0.5%, 0.75%, and 1% of bamboo fibres, the soil's shear strength was found to be reduced by 38.57%, 35.25%, 5.85%, and 38.57%, respectively. The CBR value of the soil with addition of 0.25%, 0.5%, 0.75% and 1.0%, bamboo fibers by weight of soil is found to be increased. From the limited laboratory study conducted we concluded that the 0.75% of bamboo fiber can substantially improve the properties of Black cotton soil. And thus 0.75% of bamboo fiber is the optimum fiber content for black cotton soil. The design thickness of flexible pavement before stabilization is obtained as 450mm and after stabilization is obtained as 250mm.

No. of Pages: 10 No. of Claims: 3